



XP1243 TOWEL

COMPOSITION

88% polyester / 12% Polyamide

FABRIC PROPERTIES

Usable width	.	135.0 CM
Full width	Full width	140.0 CM
Weight with a deviation of 4%	EN 12127 meth 5	190 G/M ²

PROPERTIES

Tensile Strength warp	ISO13934-1 2013	1000 N
Tensile Strength weft	ISO13934-1 2013	800 N
Tear Resistance Elmendorf warp	ISO13937-1 2000	30 N
Tear Resistance Elmendorf weft	ISO13937-1 2000	20 N
Tear Strength (3 legs) warp	ISO4674 1A 2003	50 N
Tear Strength (3 legs) weft	ISO4674 1A 2003	45 N
Air Permeability 100Pa	ISO9237-2 1995	<30 L/M ² .S
Shrinkage oven 1min-190°C - warp	shri oven 1min	2,50 %
Shrinkage oven 1min-190°C - weft	shri oven 1min	2,50 %
40°C Wash		
Tumble Dry	✓	
Dry Clean	x	
Iron	✓	

REMARKS

Treated for transfer coating, printing
Hydrophilic

The values on this sheet are solely indicative and are in no way binding for Xpres